



TRITON EPOXY HEAVY DUTY PUTTY



TECHNICAL DATA:

Specific Gravity	1.35 ± 0.05 k/l
Viscosity	
Mixing Ratio	1:1 (Component A + Component B), by volume
Drying Time	
Set-to-touch	30 minutes
Dry Through	3-4 hours
Full Cure	24 hours
Pot Life	1-2 hours
Coverage	8m ² /gal. set/ 1mm
Color	Gray
Finish	Matte
Shelf-Life	Minimum one (1) year under normal conditions.
Packaging	1L, 4L (can set)

PRODUCT DESCRIPTION:

A 2-component, heavy duty 100% epoxy-polyamide based putty specially designed for floorcoating applications used in construction, chemical and industrial. It has excellent durability, toughness, adhesion to subsequent topcoats.

PRODUCT HIGHLIGHTS:

- Has high compressive and abrasion resistance
- Can level-off uneven surfaces
- Can repair pot holes and hairline cracks

RECOMMENDED FOR:

Concrete, metal and wood





MIXING:

Mix well before use. Measure one (1) part of component A to one (1) part of component B by volume. Mix until uniform in color, apply on substrate using putty knife.

APPLICATION:

Surface Preparation

All surfaces must be thoroughly cleaned to remove dirt, grease, mill scale, loose rust, chalks, and any other contaminants that can reduce adhesion through (SSPC-SP1) solvent cleaning.

INFORMATION:

TRITON PRODUCTS are manufactured from the Highest quality raw materials using the most advanced methods. Best results from the superior product are attained when these preparation and application instructions are followed carefully.

For more information on this guide or on any Triton coating product please contact us at 8645-6203 or email us at tsr.tritonpaints@gmail.com or roosevelt.chemical.inc@gmail.com

