



TRITON MARINE ANTI-CORROSIVE PAINT



TECHNICAL DATA:

Specific Gravity	1.25 \pm 0.05 k/l
Viscosity	75 KU
Drying Time Set-to-touch Tack Free Dry Through	1 hour 4-5 hours 24 hours
Application	Brush, roller, spray
DFT (approx.)	40-50 microns/coat
Coverage	25-30 m ² /4L/coat
Reducer	Triton Marine Paint Thinner
Color	Red & Black
Finish	Sheen
Shelf-Life	Minimum one (1) year under normal conditions.
Packaging	1L, 4L

PRODUCT DESCRIPTION:

High-quality, rust inhibiting protective coating made to protect metal surfaces of marine vessels from corrosion.

PRODUCT HIGHLIGHTS:

Easy to apply, excellent corrosion resistance and adhesion that Improves overall durability of any marine vessels Long-lasting protection.

RECOMMENDED FOR:

Metal surfaces of marine vessels

RECOMMENDED SUBSTRATE:

Exterior and interior use for metal and wood





APPLICATION:

Surface Preparation and Application Method

Metal Surfaces- Acid pickling, flame cleaning, or sand blast to remove all mill scales and rust. Wipe surface with **TRITON PAINT THINNER** to remove all other contaminants. Prime the boat's hull with **TRITON ANTI- CORROSIVE PAINT** and let it dry completely for two-three (2-3) hours.

For any surface imperfection apply **TRITON NON-SAG MARINE EPOXY PART A & B** and let it dry overnight. Apply two (2) coats of **TRITON MARINE ENAMEL, TRITON MARINE BOOT-TOPPING** or **TRITON MARINE ANTI-FOULING PAINT** and let it dry overnight between coats.

Repainting of Old Metal Surfaces- Remove scale and rust particles using sandpaper and stiff bristled brush. Clean, degrease and or rinse with water, allow it to dry. Wipe surface with **TRITON PAINT THINNER** prior to applying **TRITON RUST CONVERTER. Allow to dry for one (1) hour.** Prime the boat's hull with **TRITON MARINE ANTI-CORROSIVE PAINT** and let it dry completely for two (2) hours.

Mixing

Mix well before use. Thinned down with **TRITON MARINE PAINT THINNER** up to 5% if needed.

CLEAN UP:

Use **TRITON LACQUER THINNER.**

INFORMATION:

TRITON PRODUCTS are manufactured from the highest quality raw materials using the most advanced methods. Best results from the superior product are attained when these preparation and application instructions are followed carefully.

For more information on this guide or on any Triton coating product please contact us at 8645-6203 or email us at

tsr.tritonpaints@gmail.com or
roosevelt.chemical.inc@gmail.com

