

TRITON MARINE ENAMEL



TECHNICAL DATA:

| Specific Gravity | 0.90 - 1.25 ± 0.05 k/l (depends on color) |
|---|---|
| Viscosity | 90-95 KU |
| Drying Time Set-to-touch Tack Free Dry Through | 60 minutes 2-4 hours 8-12 hours |
| Application | Brush, roller, spray |
| DFT (approx.) | 40-50 microns/coat |
| Coverage | 25-30 m ² /4L/coat |
| Reducer | Triton Marine Paint Reducer |
| Color | Refer to Triton Marine Enamel Color Chart |
| Finish | Gloss |
| Shelf-Life | Minimum one (1) year under normal conditions. |
| Packaging | 1L, 4L |

PRODUCT DESCRIPTION:

A high quality modified alkyd-based coating made to protect boat sections that are above waterline from abrasive damages arising from ship rubs with piers and fenders. It also gives an excellent protective barrier to shield surfaces against extreme weather conditions and marine environment.

PRODUCT HIGHLIGHTS:

It has high gloss, it is resistant to oil and sea water, tough and tight film and easy to apply.

RECOMMENDED FOR:

Use as finishing coat for all internal and external surfaces on boat & ship structure, and oil rig platform.

RECOMMENDED SUBSTRATE:

Metal and wooden surfaces on marine vessels and structures.





APPLICATION:

Surface Preparation and Application Method

Metal Surfaces

Clean surface to remove dust and dirt.

Wipe surface with **TRITON PAINT THINNER** to remove all other contaminants. For any surface imperfection, use **TRITON NON-SAG MARINE EPOXY** and let it dry completely overnight. Sand surface to level imperfections and improve adhesion. Prime surface with TRITON MARINE PRIMER and let it completely dry for two to three (2-3) hours. Apply two (2) coats of TRITON MARINE ENAMEL and let it dry completely for eight to ten (8-10) hours between coats.

Wooden Surfaces

Clean surface to remove dust and dirt. For any surface imperfection, use TRITON NON-SAG MARINE EPOXY and let it dry completely overnight. Sand surface to level imperfections and improve adhesion. Prime surface with TRITON MARINE EPOXY PRIMER and let it dry completely overnight. Apply two (2) coats of TRITON MARINE ENAMEL and let it dry completely overnight between coats.

Mixing

Mix well before use. Thinned down with TRITON **MARINE PAINT THINNER** up to 5% if needed.

CLEAN UP:

Use TRITON MARINE LACQUER THINNER.

Tel. Nos. 7758-6245 | 7900-9642 | 8645-6625 | 8645-1089 8645-2152 | 8645-3435 | 8645-2159 | 8645-3425

INFORMATION:

TRITON PRODUCTS are manufactured from the highest quality raw materials using the most advanced methods. Best results from the superior product are attained when these preparation and application instructions are followed carefully.

For more information on this guide or on any Triton coating product please contact us at 8645-6203 or email us at tsr.tritonpaints@gmail.com or roosevelt.chemical.inc@gmail.com

